






INTERLOCKING CONCRETE PAVEMENT SYSTEM (ICP)

DURABLE FLEXIBLE PAVEMENT SYSTEM

| STYLE | | CODE | DIMENSIONS | BANDS | CUBES |
|---|---|-------------|---|----------------------------------|-------------------------------|
| LaLosa Square 6" x 6" |  | 4LLA | 160mm x 160mm x 60mm Approximate 6¼" x 6¼" x 2⅜" (PSF = 3.69 stones @ 28#) | 12.2 SF 342# (45 stones) | 85.4 SF 2395# (7 bands) |
| LaLosa Rectangle 6" x 9" |  | 4LLB | 160mm x 240mm x 60mm Approximate 6¼" x 9⅜" x 2⅜" (PSF = 2.46 stones @ 28#) | 18.28 SF 512# (45 stones) | 91.4 SF 2559# (5 bands) |
| LaLosa Large Rectangle 9" x 12" |  | 4LLC | 240mm x 320mm x 60mm Approximate 9⅜" x 12⅝" x 2⅜" (PSF = 1.22 stones @ 28#) | 29.5 SF 835.2# (36 stones) | 88.5 SF 2506# (3 bands) |

Note: Use protective plate during compaction.

COMPOSITION & MANUFACTURE

Typical Cross Section of Concrete Paving Stone



- Borgert Pavers
- Bedding Sand 1" Thick (ASTM C33)
- Compacted Aggregate Base
Class 2 or Class 5
(Thickness depends on soil
condition and application)
- Prior to screeding the bedding sand, the base
surface tolerance must not exceed +/-1/4
in.(+/-6mm) over a 10gt. (3m) straight edge.
- Compacted Soil Subgrade

- Pavers exceed industry standards: 8,000 psi - 5% absorption
- Meets or exceeds ASTM C-936 and freeze-thaw testing per section 8 of ASTM C-67
- Manufactured with type A aggregates
- Associated with a range of LEED credits
- ADA Compliant


Written detailed specification information is available, call or visit our website at borgertproducts.com.

Edge restraint detail provided based on application.


BENEFITS OF ICP

- Flexible system, does not crack or heave in cold climates
- Easier maintenance to the pavement and utilities underneath
- Achieve endless design possibilities with different shapes, textures, colors and laying patterns
- Use slabs to delineate lines and spaces to eliminate the need to maintain paint
- Suitable for plazas and walkways. Not recommended for vehicular applications
- Borgert slabs are made with granite, creating a dense, resistant wearing course


LAYING PATTERNS




(A) Running Bond
6x6 - 66%
6x9 - 34%
Laying Ratio: 2:1




(B) Basket Weave 90°
6x6 - 30%
6x9 - 70%
Laying Ratio: 2:4




(C) Running Bond
6x6 - 40%
6x9 - 60%
Laying Ratio: 1:1




(D) 1 Piece
6x9 - 100%




(E) 1 Piece
9x12 - 100%




(F) 1 Piece
6x6 - 100%




(G) 3 Piece
6x6 - 10%
6x9 - 30%
9x12 - 60%
Laying Ratio: 1:2:2




(H) 3 Piece Random
6x6 - 18%
6x9 - 28%
9x12 - 54%
Laying Ratio: 1:1:1




(I) 1 Piece
6x9 - 100%



(J) 1 Piece
9x12 - 100%



(K) 1 Piece
9x12 - 100%



(L) 2 Piece
6x9 - 33%
9x12 - 67%
Laying Ratio: 1:1